

Amendments to the Specification

Please replace the paragraph beginning at page 4, line 18 with the following paragraph:

The thiadiazole or derivative thereof may be present in an amount of about 0.05 wt% or more. As a further example, the thiadiazole may be present in an amount of about 0.95 wt% to about 10 wt%, or in an amount of about 0.095 wt% to about 5 wt%, or in an amount of about 3 wt% to about 5 wt%, or in an amount of about 0.095 wt% to about 1 wt%, or in an amount of about 0.3 wt% to about 0.5 wt%. Further, the thiadiazole or derivative thereof may be present in an amount sufficient to provide a coefficient of friction of about 0.085 or greater in a steel-on-steel application. As a further example, the thiadiazole or derivative thereof may be present in an amount sufficient to provide a coefficient of friction of about 0.09 or greater in a steel-on-steel application.